

A1

CROSS-REFERENCE TO RELATED APPLICATION

This is a continuation-in-part of application number 08/776,868, filed on May 6, 1997. *mw*

IN THE CLAIMS

Please add new claims 22-33 as follows:

--22. Procedure for manufacturing a film of dielectric material self-adhesive by virtue of an electrostatic force, said film at least being capable of setting straight onto a surface, said film containing gas blisters wherein, to improve an adhesive quality of the film, the film is charged by means of an electric DC field intensive enough to produce partial discharges in the gas blisters and to cause the charges to move into the dielectric material of the film, creating a large unipolar charge inside the film.--

--23. Procedure as defined in claim 22, wherein the film is subjected to an AC corona treatment before charging.--

--24. Procedure as defined in claim 23, wherein the adhesion of the film is adjusted by adjusting the intensity of the AC corona treatment or the charging or both.--

--25. The procedure according to claim 22, wherein the intensity of the charging electric DC field is equal to or greater than 100mv/m.--

A2

For Office Use Only

A2

type film containing flat gas blisters, and said film containing partial discharges inside the film produced in the gas blisters to achieve an adhesive quality of the film.--

1. The first step is to identify the problem. This involves understanding the current situation and what needs to be changed.

--30. Film as defined in claim 27, wherein the film is coated with a adhesive sticky layer.--

film, the film is doped with charge binding additives.--